


Natural Fibre Centre

OFDA Micron Test Report

Date : 06Dec05 Mean = 29.28 u  
 Sample ID : MVF Autumn Gold 20Oct02 SD = 6.07 u  
 Description : F LF Hua 30Apr05 CV = 20.7 %  
 Operator : Southern Star Farm Sample size = 4000  
 Spin fineness= 28.4 u  
 Comfort factor= 62.4 %  
 Curve number = 1333  
 Curve= 33.9[25] deg/mm  
 Atong: num= 1621 M= 29.4f 5.6j Sd= 1.2k( 1.0) W(= 27.8f 5.4) b(= 3.26f 2.1)k Sml= 1.31f 1.2)k Lge= 1.9k( 1.6)k  
 OFDA166:2.14 Cal: D=5.1599\*WHH -2.98, wV= 1.4683\*wH+ -0.04, DkFlash= 83.0  
 cum.X mic count



Olds College School of Innovation - Natural Fibre Centre  
 4500 50 Street, Olds, Alberta, Canada T4H 1R6  
 relvestad@oldscollge.ab : 403-556-4683 phone