


Natural Fibre Centre

OFDA Micron Test Report

Date : 06Dec05 Mean = 21.07 u
 Sample ID : Bella Princess 21Nov04 SD = 5.43 u
 Description : F MRGr Hua 30Apr05 CV = 25.8 %
 Lot/Client : Southern Star 135461615A Sample size = 4000
 Operator : A 6798 Blanket MCR Spin fineness= 21.4 u
 5% of fibres : 9.9 u above mean. Comfort factor= 95.0 %
 Curve= 45.7[40] deg/mm Curve number = 1509

Along: num= 1685 Mn= 21.2[5.0] Sd= 0.97[0.8] Min= 19.8[4.8] bLob= 3.28[1.91% Sml= 1.39[1.01% Lge= 1.90[1.61%
 OFDA166:2.14 Cal: D=5.1599*WH -2.98, wV= 1.4683*WH+ -0.04, DkFlash= 83.0



Olds College School of Innovation - Natural Fibre Centre
 4500 50 Street, Olds, Alberta, Canada T4H 1R6
relvestad@oldscollge.ab ; 403-556-4683 phone