


OFDA Micron Test Report

Natural Fibre Centre

Date : 28Aug07
 Sample ID : RBellaPrincess 21Nov04
 Description : F MRG Hua 12May07
 Lot/Client : Southern Star Farm
 Operator : A 10633 MidSide MCR
 5% of fibres 11.4 u above mean.
 Curve= 46.5 [38] deg/mm

Mean = 25.06 u
 SD = 6.48 u
 CV = 25.9 %
 Sample size = 4000
 Spin fineness= 25.5 u
 Comfort factor= 84.7 %
 Curve number = 1355

Along: num= 1548 Mn= 25.4 [5.9] Sd= 1.09 [0.8] Min= 23.7 [5.7] blob= 3.84 [2.1] % SmL= 1.65 [1.2] % Lge= 2.20 [1.5] %
 OFDA166:2.14 Cal: D=5.1599*WH -2.98, wV= 1.4683*wH+ -0.04, DkFlash= 83.0



Olds College School of Innovation - Natural Fibre Centre
 4500 50 Street, Olds, Alberta, Canada T4H 1R6
 relvestad@oldscollege.ab ; 403-556-4683 phone