


Natural Fibre Centre

OFDA Micron Test Report

Date : 06Dec05 Mean = 24.70 u
 Sample ID : Bullet Proof 28Nov03 SD = 5.40 u
 Description : M LF Hua May05 CV = 21.9 %
 Lot/Client : Southern Star 083292358 Sample size = 4000
 Operator : A 6795 Blanket MCR Spin fineness= 24.2 u
 % of fibres : 9.6 u above mean. Comfort factor= 87.4 %
 Curve= 47.2 [34] deg/mm Curve number = 1644
 Alorg: num= 1869 Min= 24.7(5.0) Sd= 1.00(0.8) Min= 23.3(4.9) Wld= 3.02(1.8) Sml= 1.25(1.0) Lge= 1.79(1.5) %
 OFDA166:2.14 Cal: D=5.1599*WH -2.98, wV= 1.4683*wH+ -0.04, DKFlash= 83.0
 cum.% mic count



Olds College School of Innovation - Natural Fibre Centre
 4500 50 Street, Olds, Alberta, Canada T4H 1R6
 relvestad@oldscollge.ab : 403-556-4683 phone