

OFDA Micron Test Report

Natural Fibre Centre

Date : 28Aug07
 Sample ID : LF Marantha 01Oct05
 Description : F WH Hua 12May07
 Lot/Client : Southern Star Farm
 Operator : A 10613 MidSide MCR
 5% of fibres : 9.9 u above mean.
 Curve= 50.7[39] deg/mm

Mean = 21.74 u
 SD = 5.38 u
 CV = 24.8 %
 Sample size = 4000
 Spin fineness= 21.9 u
 Comfort factor= 94.1 %
 Curve number = 1280

Along: num= 1403 Mn= 21.9[5.0] Sd= 1.01[0.7] Min= 20.5[4.8] blob= 3.59[2.0]% Sml= 1.52[1.1]% Lge= 2.07[1.6] %
 OFDA166:2.14 Cal: D=5.1599*WH -2.98, wV= 1.4683*wH+ -0.04, DkFlash= 83.0

