


OFDA Micron Test Report

Natural Fibre Centre

Date : 15Sep06
 Sample ID : Pamela-Lagos 01Jan94
 Description : F DF Hua 10May06
 Lot/Client : Southern Star Farm
 Operator : A 8733 MidSide MCR
 5% of fibres 11.6 u above mean.
 Curve= 43.2[39] deg/mm

Mean = 27.32 u
 SD = 6.43 u
 CV = 23.5 %
 Sample size = 4000
 Spin fineness= 27.2 u
 Comfort factor= 77.9 %
 Curve number = 1571

Along: num= 1761 Mn= 27.3[6.0] Sd= 0.98[0.8] Min= 25.8[5.7] blob= 2.76[1.6]% Sml= 1.23[0.9]% Lge= 1.53[1.21%]
 OFDA166:2.14 Cal: D=5.1599*WH -2.98, wV= 1.4683*wH+ -0.04, DkFlash= 83.0



Olds College School of Innovation - Natural Fibre Centre
 4500 50 Street, Olds, Alberta, Canada T4H 1R6
relvestad@oldscollege.ab ; 403-556-4683 phone