

OFDA Micron Test Report

Natural Fibre Centre

Date : 28Aug07
 Sample ID : Remmington 02Dec06
 Description : M LF Hua 12May07
 Lot/Client : Southern Star Farm
 Operator : A 10617 MidSide MCR
 5% of fibres 9.9 u above mean.
 Curve= 46.7[37] deg/mm

Mean = 20.86 u
 SD = 5.79 u
 CV = 27.8 %
 Sample size = 4000
 Spin fineness= 21.6 u
 Comfort factor= 95.3 %
 Curve number = 1137

Along: num= 1253 Mn= 20.9[5.5] Sd= 1.01[0.7] Min= 19.4[5.4] blob= 3.41[1.9]% Sml= 1.47[1.0]% Lge= 1.95[1.5]%
 OFDA166:2.14 Cal: D=5.1599*WH -2.98, wV= 1.4683*wH+ -0.04, DkFlash= 83.0

