


Natural Fibre Centre

OFDA Micron Test Report

Date : 06Dec05 Mean = 17.30 u  
 Sample ID : Tucker Brown 03Oct04 SD = 5.45 u  
 Description : M MBr Hua 30Apr05 CV = 31.5 %  
 Lot/Client : Southern Star 135546132A Sample size = 4000  
 Operator : A 6794 Blanket MCR Spin fineness= 18.6 u  
 5% of fibres 10.3 u above mean. Comfort factor= 97.3 %  
 Curve= 43.2 [37] deg/mm Curve number = 1312

Atong: num= 1392 Mn= 17.4 [ 5.2] Sd= 0.83 [ 0.6] Min= 16.2 [ 5.0] biob= 3.46 [ 2.0] Sm= 1.48 [ 1.0] Lge= 1.99 [ 1.8] %  
 OFDA166:2.14 Cal: D=5.1599\*WH -2.98, wV= 1.4683\*WH+ -0.04, DkFlash= 83.0



Olds College School of Innovation - Natural Fibre Centre  
 4500 50 Street, Olds, Alberta, Canada T4H 1R6  
[relvestad@oldscollege.ab](mailto:relvestad@oldscollege.ab) ; 403-556-4683 phone