

# OFDA Micron Test Report


## Natural Fibre Centre

Date : 28Aug07  
 Sample ID : CWP Savannah 14Sep02  
 Description : F MB Hua 12May07  
 Lot/Client : Southern Star Farm  
 Operator : A 10630 MidSide MCR  
 5% of fibres 11.2 u above mean.  
 Curve= 41.4[32] deg/mm

Mean = 31.95 u  
 SD = 6.16 u  
 CV = 19.3 %  
 Sample size = 4000  
 Spin fineness= 30.7 u  
 Comfort factor= 42.7 %  
 Curve number = 1253

Along: num= 1629 Mn= 32.7[ 5.7] Sd= 1.50[ 1.1] Min= 30.4[ 5.4] blob= 3.88[ 2.1]% Sml= 1.58[ 1.3]% Lge= 2.29[ 1.6]%

OFDA166:2.14 Cal: D=5.1599\*WH -2.98, wV= 1.4683\*wH+ -0.04, DkFlash= 83.0



Olds College School of Innovation - Natural Fibre Centre  
 4500 50 Street, Olds, Alberta, Canada T4H 1R6  
 relvestad@oldscollge.ab ; 403-556-4683 phone